

# Druck - Temperatur - Tabelle

## Pressure - Temperature Rating



Material: 1.0566 / P355NL1 / A350 Gr.LF2

Temp. [°C]	Temp [°F]	PN 25		PN 40		PN 63		PN 100		PN 160	
		[bar]	[psi]	[bar]	[psi]	[bar]	[psi]	[bar]	[psi]	[bar]	[psi]
-40,0		25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
-10,0		25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
RT	68,0	25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
50,0	122,0	25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
100,0	212,0	25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
120,0	248,0	25,0	362,5	40,0	580,0	63,0	913,5	100,0	1450,0	160,0	2320,0
150,0	302,0	24,0	348,0	38,0	551,0	59,0	855,5	93,0	1348,5	145,0	2102,5
200,0	392,0	23,0	333,5	36,0	522,0	55,0	797,5	85,0	1232,5	130,0	1885,0
250,0	482,0	21,0	304,5	33,0	478,5	48,0	696,0	74,0	1073,0	113,0	1638,5
300,0	572,0	18,0	261,0	30,0	435,0	41,0	594,5	62,0	899,0	96,0	1392,0

